


ANALYSIS: Coefficient of Friction Per ASTM C1028

Table #1

Sample #	Dry (Load, Lbs.)		Wet (Load, Lbs.)	
	<u>Static</u>	<u>Dynamic</u>	<u>Static</u>	<u>Dynamic</u>
	40.5	32.5	42.0	37.0
	40.0	32.5	42.0	37.5
	38.5	37.0	43.5	36.0
	41.0	35.0	45.0	36.0
	41.0	31.5	39.0	35.5
	37.5	33.0	41.5	38.0
	37.0	33.0	41.5	37.0
	35.5	33.0	40.5	35.5
	40.5	30.5	39.0	37.0
	36.5	34.0	42.0	36.5
	36.6	34.0	43.5	39.0
	37.5	32.0	42.5	39.0
Avg.	38.46	33.17	41.84	37.0
C.O.F.	0.74	0.64	0.81	0.72

This report applies only to the actual samples tested. Northwest Laboratories does not certify, warrant, or guarantee any products manufactured by others. Samples will be discarded within **(30) days** unless otherwise requested in writing by you.

NORTHWEST LABORATORIES, INC.



 Simon, Chemist